

DECLARATION OF PERFORMANCE
Nr. 2025-06-14

1. Unique product type identifier:

POINT Penoplast

2. The type, batch or serial number or any other element by which the construction product can be identified:

The batch number is indicated on the packaging.

3. The intended use or uses of the construction product by the manufacturer in accordance with the applicable technical specification:

All-season polyurethane foam adhesive

4. Name of the manufacturer, registered trade name or registered trademark and manufacturer's contact address, factory address:

UAB TEGRA STATE

Savanoriu ave 178A, LT-03154 Vilnius, LITHUANIA

Tel.:+37052661167

www.tegrastate.eu

E-mail: info@tegragroup.eu

5. Where applicable, the name and address of the authorised representative with the powers laid down in Article 18(15) of the Law on Construction of the Republic of Lithuania: Not applicable

6. A system or systems for assessing and verifying the constancy of performance of the construction product as set out in Chapter V of this Regulation:

System 3

System 4

7. Name of the certification body or testing laboratory:

Notified body: 2164

8. Declared performance:

CONDITIONING:

ACCORDING TO TS EN 17333; 23 °C & 50% RELATIVE HUMIDITY

SUBSTRATE:

17333-4 METHOD 1 => P3 TYPE PLYWOOD

17333-4 METHOD 2 => P3 TYPE PLYWOOD

17333-4 METHOD 3 => PINE WOOD

17333-4 METHOD 5 => DIN EN 204 205 - BEECH WOOD (10x20 adhesion area)

Essential Characteristic	Declared Performance	Harmonized Standard
Joint Foam Density	17,53 kg/m ³	EN 17333-1 (Method 1)
Foam Yield	10,88 m (3x10 cm joint) 36,27 m (3x3 cm joint)	EN 17333-1 (Method 1)
Total Foam Yield	44,89 L	EN 17333-1 (Method 2)
Free Foamed Density	19,47 kg/m ³	EN 17333-1 (Method 3)
Dimensional Stability	Avg: -1,34%	EN 17333-2 (Method 1)
Curing Pressure	5,33 kPa	EN 17333-2 (Method 2)
Post Expansion	47,37%	EN 17333-2 (Method 3)
Cutting Time	30 min	EN 17333-3 (Method 1)
Tack Free Time	6 min	EN 17333-3 (Method 2)
Sagging	Non Sag for 5 cm Joint Width	EN 17333-3 (Method 3)
Compression Strength	50,25 kPa	EN 17333-4 (Method 1)
Tensile Strength	79,35 kPa	EN 17333-4 (Method 2)
Shear Strength	55,68 kPa	EN 17333-4 (Method 3)
Bonding Strength	9,08 MPa	EN 17333-4 (Method 5)
Insulation	0,0285 W/m.K	EN 17333-5

9. the performance of the product referred to in clauses 1 and 2 shall be in accordance with the performance declared in clause 8.

10. Signed (by and on behalf of the manufacturer):

Vilnius 2025.06.14

 (Signature)

The stamp is circular and contains the text: "UAB 'Bendrasis Tegravimas'", "Dokumentams", "Nr. 1", and "VILNIUS".

*Eksplotacinių savybių deklaracija parengta pagal „STATYBOS TECHNINĮ REGLAMENTĄ STR 1.01.04:2015“